

CERTIFICATE OF ANTIBACTERIAL ANALYSIS

CERTIFICATE NO.	BC004/2023	DATE RECEIVED	13.01.2023
CUSTOMER	SCHMITZ UND SÖHNE GMBH	DATE ANALYSED	17.01.2023
CUSTOMER REF.	230/024-025	DATE REPORTED	23.01.2023
UNITS OF RESULTS	Colony Forming Units	NO. OF PAGES	1 of 1

METHOD OF ANALYSIS: DETERMINATION OF ANTIBACTERIAL ACTIVITY USING ISO 22196:2011

SAMPLE	TEST ORGANISM	CONTACT TIME		REDUCTION (INITIAL)	
		0 HRS	24 HRS	Log ₁₀	%
AKZONOBEL RAL 9002 GREY WHITE. BATCH I.D. YL 13798 HQ	MRSA	9.29E+04	≤100	≥2.97	≥99.89%
AKZONOBEL RAL 9002 GREY WHITE. BATCH I.D. YL 13798 HQ	<i>E. coli</i>	9.35E+04	≤100	≥2.97	≥99.89%
AKZONOBEL RAL 9010 PURE WHITE. BATCH I.D. YE 39500 HQ	MRSA	9.29E+04	≤100	≥2.97	≥99.89%
AKZONOBEL RAL 9010 PURE WHITE. BATCH I.D. YE 39500 HQ	<i>E. coli</i>	9.35E+04	≤100	≥2.97	≥99.89%

The above data describe the difference in the population sizes of the test organisms, relative to the initial (0 hours) population, following contact with the surface of the samples detailed in this CoA for 24 hours at 35°C under a RH of >90%. These conditions are those specified by the ISO 22196: 2011 method of analysis.

Comment: The samples AKZONOBEL RAL 9002 GREY WHITE. BATCH I.D. YL 13798 HQ and AKZONOBEL RAL 9010 PURE WHITE. BATCH I.D. YE 39500 HQ have achieved the BioCote minimum antibacterial performance requirement of 95% "Reduction against the initial for *E. coli* and MRSA" according to ISO 22196: 2011 analysis.

FOR BIOCOTE LTD



Technical Manager
 Parmjit S Bilan